

TEST REPORT

REPORT NUMBER : TURT130108497
APPLICANT NAME Uçar Oyuncak San.ve Tic.Ltd.Şti.
ADDRESS Hadımköy Ömerli Mah.İstanbul Yolu Cad. No:195 Arnavutköy İstanbul TÜRKİYE
FAX NO :0212 798 27 52
Attention :Burcu Denizergi (export@ucaroyuncak.com)
BUYER NOT GIVEN
SAMPLE DESCRIPTION : One sample of yellow/purple/pink/fuchsia 18 pcs plastic kitchen set
DATE IN : 16 July, 2013 (11:13)
DATE OUT : 29 July, 2013
ITEM NO: 142
YOUR REFERENCE: PRINCESS MAYA & FRIENDS KITCHEN SET
AGE GRADING: 3 YEARS AND ABOVE
COUNTRY OF ORIGIN: TURKEY
NOTE: In this report, Toxic Elements Analysis and Total Phthalate Content tests results were taken from report number TURT130108487 dated on 29 July, 2013 by the request of the applicant.

TEST	Sample
SAFETY OF TOYS-PART 1:MECHANICAL AND PHYSICAL PROPERTIES	P (Except 7.1)
SAFETY OF TOYS-PART 2:FLAMMABILITY	P
TOXIC ELEMENTS ANALYSIS	P
TOTAL PHTHALATE CONTENT	P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.S.

The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and UKAS accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation. Tests marked (*) in this test report are not included in the UKAS accreditation schedule for this laboratory.



Beril SEN
COORDINATOR



Sinan Öncel
Customer Care Manager



2111

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55
e-mail : labtest.turkey@intertek.com
www.intertek-turkey.com



130108497

Test Method	Result	Requirements
-------------	--------	--------------

This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

Specification: BS EN 71-1: 2011- Safety of Toys - Specification for Mechanical and Physical Properties

The item was labelled “Warning! Contain small and swallowed parts.

Not suitable for children under 3 years due to choking hazard”.

The item was tested for children aged over 36 months.

The item was packaging in a cardboard box with a flexible plastic window which was considered to be disposable.

SECTION	TEST	RESULTS
4	General Requirements	
4.1	Material	Pass
4.7	Edges	Pass
4.8	Points & Metallic Wires	Pass
4.11	Mouth-Actuated Toys and Other Toys Intended to be Put in the Mouth	
	a) Toy intended to be put in the mouth, removable mouth pieces and other removable components of toys intended to be put in the mouth	Pass
	b) Mouthpieces and other components of toys intended to be put in the mouth – After soaking	Pass
7	Warning and Instruction for Use	
7.1	<p>General</p> <p>The toy or, its packaging or document accompanying must be labelled with:</p> <ul style="list-style-type: none"> - The name and address of the importer.** - A CE mark in the correct shape. - Warning and other information should be in the national language(s) of the countries where the toy is marketed. <p>**In the case of the toy sell in European countries, the toy, its packaging or document accompanying must be labelled with the name and address of the manufacturer and importer.</p>	See Comment
7.2	Toys not intended for children under 36 months	Pass



Test Method	Result	Requirements
-------------	--------	--------------

(*)Specification: BS EN 71-2: 2011 Safety of Toys – Flammability

SECTION	TEST	RESULTS
4.1	General	
	Celluloid/cellulose nitrate and materials with a same burning behaviour in fire	Pass



2111

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Light pink granule	<u>RESULT (ppm)</u>	<u>PASS/FAIL</u>	<u>REQUIREMENT (ppm)</u>
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	2 ppm	PASS	70000
Boron (B)	0.2 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.5 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.7 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	2.2 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Black granule	RESULT (ppm)	PASS/FAIL	REQUIREMENT (ppm)
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	7 ppm	PASS	70000
Boron (B)	< 0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.5 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.2 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	3.2 ppm	PASS	46000

ppm (Part per million)

<

ND

Detection Limit

=mg / kg

=Less Than

=Not Detected

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

White granule	RESULT (ppm)	PASS/FAIL	REQUIREMENT (ppm)
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	1.2 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	1.4 ppm	PASS	70000
Boron (B)	< 0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.5 ppm	PASS	7700
Manganese (Mn)	0.6 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	4.3 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	0.5 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Red granule	RESULT (ppm)	PASS/FAIL	REQUIREMENT (ppm)
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.2 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	0.7 ppm	PASS	70000
Boron (B)	0.3 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	1 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	4.6 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	10.7 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

<u>Navy granule</u>	<u>RESULT (ppm)</u>	<u>PASS/FAIL</u>	<u>REQUIREMENT (ppm)</u>
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	0.3 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	242.9 ppm	PASS	70000
Boron (B)	1.8 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.1 ppm	PASS	7700
Manganese (Mn)	0.6 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.7 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	38.6 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Purple granule	RESULT (ppm)	PASS/FAIL	REQUIREMENT (ppm)
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	0.2 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	214.7 ppm	PASS	70000
Boron (B)	1.7 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.1 ppm	PASS	7700
Manganese (Mn)	0.4 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	2.6 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	34.5 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements	
(*) Toxic Elements Analysis			
PR EN 71-3 : 2013			
Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)			
Grey granule	RESULT (ppm)	PASS/FAIL	
		REQUIREMENT (ppm)	
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	6.6 ppm	PASS	70000
Boron (B)	< 0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.3 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	2.8 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	3.1 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements	
(*) Toxic Elements Analysis			
PR EN 71-3 : 2013			
Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)			
Green granule	<u>RESULT (ppm)</u>	<u>PASS/FAIL</u>	
		<u>REQUIREMENT (ppm)</u>	
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	0.5 ppm	PASS	70000
Boron (B)	0.2 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.7 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	4.3 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	9.8 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements	
(*) Toxic Elements Analysis			
PR EN 71-3 : 2013			
Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)			
Orange granule	RESULT (ppm)	PASS/FAIL	
		REQUIREMENT (ppm)	
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	2.8 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	2.9 ppm	PASS	70000
Boron (B)	0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.6 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	4 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	2.2 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Yellow granule	<u>RESULT (ppm)</u>	<u>PASS/FAIL</u>	<u>REQUIREMENT (ppm)</u>
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	2.3 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	2.7 ppm	PASS	70000
Boron (B)	0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.2 ppm	PASS	7700
Manganese (Mn)	0.5 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.5 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	1.7 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements	
(*) Toxic Elements Analysis			
PR EN 71-3 : 2013			
Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)			
Blue granule	RESULT (ppm)	PASS/FAIL	
		REQUIREMENT (ppm)	
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	1.1 ppm	PASS	70000
Boron (B)	< 0.1 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.5 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.8 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	22.2 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

(*) Toxic Elements Analysis

PR EN 71-3 : 2013

Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)

Pink granule	<u>RESULT (ppm)</u>	<u>PASS/FAIL</u>	<u>REQUIREMENT (ppm)</u>
Antimony (Sb)	< 0.1 ppm	PASS	560
Arsenic (As)	< 0.1 ppm	PASS	47
Barium (Ba)	< 0.1 ppm	PASS	18750
Cadmium (Cd)	< 0.1 ppm	PASS	17
Chromium (III)	< 0.1 ppm	PASS	460
Chromium (VI)	< 0.1 ppm	PASS	0,2
Lead (Pb)	< 0.1 ppm	PASS	160
Mercury (Hg)	< 0.01 ppm	PASS	94
Selenium (Se)	< 0.1 ppm	PASS	460
Aluminium (Al)	1.7 ppm	PASS	70000
Boron (B)	0.2 ppm	PASS	15000
Cobalt (Co)	< 0.1 ppm	PASS	130
Copper (Cu)	0.4 ppm	PASS	7700
Manganese (Mn)	0.4 ppm	PASS	15000
Nickel (Ni)	< 0.1 ppm	PASS	930
Strontium (Sr)	3.6 ppm	PASS	56000
Tin (Sn)	< 0.1 ppm	PASS	180000
Organic tin	< 0.1 ppm	PASS	12
Zinc (Zn)	1.9 ppm	PASS	46000

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
(*) Toxic Elements Analysis		
PR EN 71-3 : 2013		
Acid extraction method determined by Inductively Coupled Plasma – Mass Spectrometer (ICP / MS)		
Fuchsia granule	RESULT (ppm)	PASS/FAIL
		REQUIREMENT (ppm)
Antimony (Sb)	< 0.1 ppm	PASS
Arsenic (As)	< 0.1 ppm	PASS
Barium (Ba)	< 0.1 ppm	PASS
Cadmium (Cd)	< 0.1 ppm	PASS
Chromium (III)	< 0.1 ppm	PASS
Chromium (VI)	< 0.1 ppm	PASS
Lead (Pb)	< 0.1 ppm	PASS
Mercury (Hg)	< 0.01 ppm	PASS
Selenium (Se)	< 0.1 ppm	PASS
Aluminium (Al)	0.9 ppm	PASS
Boron (B)	< 0.1 ppm	PASS
Cobalt (Co)	< 0.1 ppm	PASS
Copper (Cu)	0.4 ppm	PASS
Manganese (Mn)	0.5 ppm	PASS
Nickel (Ni)	< 0.1 ppm	PASS
Strontium (Sr)	2.9 ppm	PASS
Tin (Sn)	< 0.1 ppm	PASS
Organic tin	< 0.1 ppm	PASS
Zinc (Zn)	18.3 ppm	PASS

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

Detection Limit

=Mercury (Hg): <0.01 ppm, Others metal: <0.1 ppm



2111

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

www.intertek-turkey.com

Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

1- Composite sample of light pink granule, light pink plastic, black granule, black plastic, white granule	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



2111

Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

2- Composite sample of white plastic, red granule, red plastic, navy granule, navy plastic	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

3- Composite sample of purple granule, purple plastic, grey granule, grey plastic, green granule	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



2111

Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

4- Composite sample of green plastic, orange granule, orange plastic, yellow plastic, yellow granule	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

5- Composite sample of blue granule, blue plastic, pink granule	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



2111

Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

6- Composite sample of pink plastic, fuchsia granule, fuchsia plastic	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------



END OF TEST REPORT



2111